


CARACTERISTICI PRODUS: HARDSCAPE-PORCELAIN-TOTAL		CARACTERISTICI TEHNICE	STANDARD	LIMITE STABILITE		L'ALTRA PIETRA®
REGULARITATE		LUNGIME SI LATIME	ISO 10545-2	± 0.6 %	± 2 mm	CONFORM
		GROSIME	ISO 10545-2	± 5.0 %	± 0,5 mm	CONFORM
		RECTANGULARITATE	ISO 10545-2	± 0.5 %	± 2 mm	CONFORM
		RECTITUDINEA LATURILOR	ISO 10545-2	± 0.5 %	± 1,5 mm	CONFORM
		PLATITUDINEA SUPRAFETEI	ISO 10545-2	± 0.5 %	± 2 mm	CONFORM
STRUCTURA		ABSORBTIE APA	ISO 10545-3	≤ 0.5 %		< 0.1 %
		REZISTENTA LA RUPERE	ISO 10545-4	≥ 1300 N		≥ 9000 N
		MODULUL DE RUPERE	ISO 10545-4	≥ 35 N/mm²		≥ 43 N/mm²
TERMO-HIGROMETRIC		EXPANSIE TERMICA LINEARA	ISO 10545-8	VALOARE DECLARATA		$\alpha \leq 6 \cdot 10^{-6} \text{ }^{\circ}\text{C}$
		REZISTENTA LA SOC TERMIC	ISO 10545-9	TEST VALIDAT		GARANTAT
		REZISTENTA LA INGHET	ISO 10545-12	TEST VALIDAT		GARANTAT
CHIMIC		REZISTENTA LA SUBSTANTE CHIMICE(ACIZI, BAZE SI SARURI)	ISO 10545-13	UB MINIM		GARANTAT
		REZISTENTA LA PETE	ISO 10545-14	≥ 3		5 GARANTAT

PIATRA ONLINE

021 9907 / office@piatraonline.ro

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

SIGURANTA		REZISTENTA LA ALUNECARE	DIN 51130	VALOARE DECLARATA	R11
			DIN 51097		A+B+C
		REACTIE LA FOC	EN 13501-1	CLASA DECLARATA	A1 FL / A1

In conformitate cu standardele EN 14411 (ISO 13006) anexa G grupul
Bla