

PIATRA ONLINE

021 9907 / office@piatraonline.ro

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

CARACTERISTICI: L'ALTRA-PIETRA-PORCEA		CARACTERISTICI TEHNICE	STANDARD	LIMITE STABILITE		L'ALTRA PIETRA®
REGULARITATE		LUNGIME SI LATIME	ISO 10545-2	± 0.6 %	± 2 mm	CONFORM
		GROSIME	ISO 10545-2	± 5.0 %	± 0,5 mm	CONFORM
		RECTANGULARITATE	ISO 10545-2	± 0.5 %	± 2 mm	CONFORM
		RECTITUDINEA LATURILOR	ISO 10545-2	± 0.5 %	± 1,5 mm	CONFORM
		PLATITUDINEA SUPRAFEȚEI	ISO 10545-2	± 0.5 %	± 2 mm	CONFORM
STRUCTURA		ABSORBTIE DE APA	ISO 10545-3	≤ 0.5 %		CONFORM
		REZISTENTA LA RUPERE	ISO 10545-4	≥ 1300 N		≥ 10000 N
		MODULUL DE RUPERE	ISO 10545-4	≥ 35 N/mm²		≥ 35 N/mm²
SUPRAFATA		REZISTENTA LA ABRAZIUNE	ISO 10545-7	VALOARE DECLARATA		CLASA 4 (2100 rpm) CLASSE 4 (2100 rpm) KLASS 4 (2100 rpm) CLASSE 4 (2100 rpm)
TERMO-HIGROMETRIC		EXPANSIUNE TERMICA LINEARA	ISO 10545-8	VALOARE DECLARATA		< 7x10 ⁻⁶ °C ⁻¹ (1)
		REZISTENTA LA SOC TERMIC	ISO 10545-9	TEST VALID		GARANTAT
		REZISTENTA LA INGHET	ISO 10545-12	TEST VALID		GARANTAT
CHIMIC		REZISTENTA LA PRODUSE CHIMICE (ACIDI, BAZE SI SARURI)	ISO 10545-13	UB MINIM		UA ULA GARANTAT

PIATRA ONLINE

021 9907 / office@piatraonline.ro

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

		REZISTENTA LA PETE	ISO 10545-14	≥ 3	GUARANTEED GARANTITO GARANTIERT GARANTI
SIGURANTA		COEFICIENT DINAMIC DE FRECARA	BCRA	> 0.4	> 0.4
		REZISTENTA LA ALUNECARE	DIN 51130	VALOARE DECLARATA	R11

In conformitate cu standardele EN 14411 (ISO 13006) anexa G grupul