

CARACTERISTICI: L'ALTRA PIETRA® TORRE		CARACTERISTICI TEHNICE	STANDARD	LIMITE STABILITE		L'ALTRA PIETRA®
REGULARITATE		LUNGIME SI LATIME	ISO 10545-2	± 0.6 %	± 2 mm	CONFORM
		GROSIME	ISO 10545-2	± 5.0 %	± 0,5 mm	CONFORM
		RECTANGULARITATE	ISO 10545-2	± 0.5 %	± 2 mm	CONFORM
		RECTITUDINEA LATURILOR	ISO 10545-2	± 0.5 %	± 1,5 mm	CONFORM
		PLATITUDINEA SUPRAFETEI	ISO 10545-2	± 0.5 %	± 2 mm	CONFORM
STRUCTURA		ABSORBTIE DE APA	ISO 10545-3	≤ 0.5 %		<0,1 %
		REZISTENTA LA RUPERE	ISO 10545-4	≥ 1300 N		≥10000 N
		MODUL DE RUPERE	ISO 10545-4	≥ 35 N/mm²		>35 N/mm²
TERMO-HIGROMETRIC		REZISTENTA LA SOC TERMIC	ISO 10545-9	TEST VALID		GARANTAT
		REACTIE LA FOC	EN 14411	TEST VALID		A1 FL / A1
CHIMIC		REZISTENTA LA PRODUSE CHIMICE (ACIDI, BAZE SI SARURI)	ISO 10545-13	UB MINIM		UA ULA UHA
		REZISTENTA LA PETE	ISO 10545-14	VALOARE DECLARATA		5 GARANTAT
SIGURANTA		COEFICIENT DE FRECARA DINAMICĂ UMEDĂ	DIN 51130	VALOARE DECLARATA		R11

In conformitate cu standardele EN 14411 (ISO 13006) anexa G grupul Bla UGL